

Appl. No. 10/676,397  
Atty. Docket No. 9047MQ  
Amdt. dated February 2, 2006  
Reply to Office Action of September 2, 2005  
Customer No. 27752

### AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) A tissue paper product comprising one or more plies of a tissue paper; wherein at least one of the plies comprises cellulose and from about 0.005% to about [[0.14%]] 0.1% by weight based on the weight of cellulose of xylan.
2. (Original) A tissue product according to Claim 1 wherein at least one of the plies comprises from about 0.015% to about 0.1% by weight, based on the weight of cellulose of xylan.
3. (Original) A tissue product according to Claim 1 wherein at least one of the plies comprises from about 0.02% to about 0.05% by weight, based on the weight of cellulose of xylan.
4. (Original) A tissue product according to Claim 1 wherein the source of the xylan is from about 0.1% to about 10% of highly refined pulp refined to have a Canadian Standard Freeness measurement less than about 350 and a Schopper-Riegler slowness value greater than about 35 °SR.
5. (Original) A tissue product according to Claim 4 wherein the highly refined pulp has a Canadian Standard Freeness measurement less than about 100 and a Schopper-Riegler slowness value of from about 60°SR to about 80°SR
6. (Original) A tissue product according to Claim 5 wherein the pulp is birch pulp.
7. (Original) A tissue product according to Claim 1 further comprising from about 0.1 kg/ton to about 2 kg/ton of a cationic charge biasing species.
8. (Original) A tissue product according to Claim 6 further comprising from about 0.1 kg/ton to about 2 kg/ton of a cationic charge biasing species.
9. (Withdrawn) A method for the manufacture of hygienic cellulose paper comprising the steps of:
  - a) producing a furnish comprising cellulose;

Appl. No. 10/676,397  
Atty. Docket No. 9047MQ  
Amdt. dated February 2, 2006  
Reply to Office Action of September 2, 2005  
Customer No. 27752

- b) adding from about 0.005% to about 0.14% by weight, based on the weight of cellulose, xylan to the furnish;
  - c) forming the furnish into a paper web
  - d) drying the paper web; and
  - e) creping the dried paper web.
10. (Withdrawn) A method for the manufacture of hygienic cellulose paper according to Claim 9 wherein the xylan addition step occurs before the paper web forming step.
11. (Withdrawn) A method for the manufacture of hygienic cellulose paper according to Claim 9 wherein the xylan addition step occurs during the paper web forming step.
12. (Withdrawn) A method for the manufacture of hygienic cellulose paper according to Claim 9 wherein the xylan is added in the form of a powder having an activity ranging from about 60% to about 80%.
13. (Withdrawn) A method for the manufacture of hygienic cellulose paper according to Claim 9 wherein the xylan is added in the form of a highly refined sulfate pulp mixture having a Canadian Standard Freeness measurement less than about 350 and a Schopper-Riegler slowness value of from about 35 °SR to about 90°SR.
14. (Withdrawn) A method for the manufacture of hygienic cellulose paper according to Claim 13 wherein the pulp is birch.
15. (Withdrawn) A method for the manufacture of hygienic cellulose paper according to Claim 9 wherein the xylan is added in the form of a concentrated liquor.
16. (Withdrawn) A method for the manufacture of hygienic cellulose paper according to Claim 6 also comprising the step of adding from about 0.1 kg/ton finished paper to about 2 kg/ton of a cationic charge biasing species to the furnish.